

陶瓷纖維 噴吹式 棉毯

陶瓷纖維 離心式 棉毯



產品名稱		1260°C-S 棉毯	1400°C-S 棉毯	1600°C 棉毯
最高使用溫度		1260°C 2300°F	1425°C 2600°F	1593°C 2900°F
標稱密度 (Kg/M3)		6P, 8P 96, 128	6P, 8P 96, 128	6P, 8P 96, 128
尺寸 (mm)		6x600x7200, 13x600x7200 25x600x7200 50x600x3600	25x600x7200 50x600x3600	12.5x600x3600 25x600x3600
Kg/cm2 伸張強度	4P 64KG/M ³	0.4	0.4	-----
	6P 96KG/M ³	0.8	0.8	0.95
	8P 128KG/M ³	1.05	1.05	1.05
Kcal/mh°C 熱傳導率	密度	6P 8P	6P 8P	6P 8P
	400°C	0.0946 0.086	0.0945 0.086	0.0688 0.0688
	600°C	0.1376 0.129	0.1376 0.129	0.1118 0.1032
	800°C	0.1978 0.172	0.1978 0.172	0.1634 0.1462
	1000°C	0.2752 0.2322	0.2752 0.2322	0.2322 0.2064
	1200°C	-----	-----	0.387 0.3268
1400°C	-----	-----	0.5762 0.4816	
化學成份%	AL ₂ O ₃	46	43	96
	SiO ₂	54	54	4
	ZrO ₂	-----	-----	-----
	CaO	-----	-----	-----
	MgO	-----	-----	-----
	Cr ₂ O ₃	-----	3	-----
	其它	微量	微量	-----

6mmt 僅密度 8P 的棉毯可提供

Your Solution for Insulation Since 1989 !